



## 5700GP FIBERGLASS BODY FILLER

ET5700GP-300, 3kg green

ET5700GP-100, 1kg green



### Product

2K polyester glassfiber reinforced body filler for leveling and bridging of cracks, small holes and rusted through areas in automotive, industrial and marine industries.



### Substrates

Good adhesion on iron, steel, aluminum, zinc and GRP.



### Surface Preparation

Clean, flatten, derust and degrease the surface.



### Application Conditions

From 10° C



### Mixing

2-3% with hardener



### Specific weight

1.60 kg/l



### Pot Life

4-5 min at 20°C



### Number of layers

Can be applied in several thin layers.



### Drying

20-25 min at 20°C



### Drying with IR lamps

8-10 min



### Sanding

Dry sanding only P80-P120

### Shelf life

12 months