



UNDERBODY COATING

ET/UC-1000B 1kg, black ET/UC-1000G 1kg, grey ET/UC-1000W 1kg, white

Product	An overpaintable rubber based stone chip protective coating with anti-corrosion and sound-deadening properties. After drying a durable and elastic film remains. Can be overpainted with all existing automotive coatings.
Substrates	Underbody vehicle parts like bumpers, front and rear aprons, doorsills, chassis etc
Surface Preparation	The surface to be treated must be clean, dry, rust-, dust-, grease free
Application Conditions	18-22° C
Mixing	Ready to use
Spraying Equipment	Underbody coating gun with a pressure 5-6 Bar
Number of Layers	1-2 coats
Flash off	5-10 min
Drying	2 hours at 20° C or 45 min at 60° C
VOC	< 840g/l compliant with EU 2004/42/EC directive
Shelf life	24 months

Technical Data Sheet etalon-refinish.com