



## 9900 2:1 SR HS **CLEARCOAT**

ET9900-SRHS011L ET9900-SRHS05 5L

	Product	2K scratch resistant high solids acrylic clearcoat. Non-yellowing UV resistant formula, crystal transparency.
	Substrates	Apply on top of fully dry solvent and waterborne basecoats
	Surface Preparation	The use of tack cloth is recommended prior application
	<b>Application Conditions</b>	18-22°C
	Mixing	2:1 by volume with Etalon 9901 hardener slow, normal, fast.
	Dilution	0-6%
	Pot Life	60min at 20°C
s	<b>Application Viscosity</b>	15-18 sec at 20°C Ford cup 4
*	Spraying Equipment	Gravity feed spray gun 1.3mm
	Number of layers	2 coats
/ <sub>1</sub> / <sub>1</sub> / <sub>1</sub>	Flash off	10-12min
	Coating Thickness	45-50 μm
	Drying	35-40min at 60°C Touch dry: 5-6hours at 20°C Full dry: 14hours
	Drying with IR lamps	7-10min with 15min flash off time
	VOC	2004/42/IIB€(840)<840
	Shelf life	Clearcoat: 24months Hardener: 12months

Technical Data Sheet etalon-refinish.com